

TECHNICAL DATA SHEET

AXIS (REGULAR)

PHYSICAL AND CHEMICAL PROPERTIES

StructureCalcined

Screen Analysis

+ 6 Mesh	5.0%
+ 10 Mesh	54.0%
+ 20 Mesh	87.0%
+ 80 Mesh	99.8%
- 80 Mesh	0.2%

Pore Size Range (microns)0.1 – 1

pH (10% slurry).....7.0

Hardness (psi)180

Density:	(lb/ft ³)	(g/l)
Dry Bulk.....	25	400

Water Absorption (Westinghouse) lbs/100lbs.....112

Updated: 03/2007

UNCONTROLLED COPY FOR INFORMATION PURPOSES ONLY.
All information shown is typical – **NOT TO BE USED FOR SPECIFICATIONS.**
Read appropriate Material Safety Data Sheet before using.
Contact EP Minerals for product specification approval.